

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : C12N 15/10, B01J 20/28, B01D 15/08	A1	(11) International Publication Number: WO 00/15778 (43) International Publication Date: 23 March 2000 (23.03.00)
(21) International Application Number: PCT/US99/20596 (22) International Filing Date: 8 September 1999 (08.09.99) (30) Priority Data: 09/154,529 16 September 1998 (16.09.98) US (71) Applicant: VARIAN, INC. [US/US]; 3120 Hansen Way, D-102, Palo Alto, CA 94304 (US). (72) Inventor: HATCH, Richard; 1254 Burnett Street, Berkeley, CA 94702 (US). (74) Agents: FISHMAN, Bella et al.; Varian, Inc., Legal Dept., 3120 Hansen Way, D-102, Palo Alto, CA 94304 (US).		(81) Designated States: CA, CN, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: MONOLITHIC MATRIX FOR SEPARATING NUCLEIC ACIDS BY REVERSE-PHASE ION-PAIR HIGH PERFORMANCE LIQUID CHROMATOGRAPHY (57) Abstract <p>The present invention provides monolithic polymer matrices for the separation of bio-organic molecules by liquid chromatography. In one embodiment, the matrix is formed from a polymerization mixture including (i) a hydrophobic monomer, (ii) a crosslinking agent, and (iii) a porogenic solvent or mixture of porogenic components. The monolithic matrices of the invention are particularly useful for resolving polynucleotides (e.g., DNA and/or RNA) in samples by way of reversed-phase ion-pairing chromatography.</p> <div data-bbox="529 1171 1369 1631" data-label="Figure"> <p>The figure is a chromatogram plot with the x-axis representing time in minutes, ranging from 0.0 to 15.0. A single, prominent, sharp peak is visible at approximately 10.5 minutes. The baseline is relatively flat with minor noise. The peak height is significant, reaching about 80% of the maximum y-axis scale.</p> </div>		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

MONOLITHIC MATRIX FOR SEPARATING NUCLEIC ACIDS BY REVERSE-PHASE ION-PAIR
HIGH PERFORMANCE LIQUID CHROMATOGRAPHY

5 **FIELD OF THE INVENTION**

The present invention relates to the separation of bio-organic molecules. In particular, the invention provides a monolithic polymer matrix for the separation of polynucleotides by reversed-phase ion-pairing chromatography.

10 **BACKGROUND OF THE INVENTION**

Polynucleotide separations have become increasingly important in recent years. Separating polynucleotide species contained in a sample is useful, for example, in the detection and/or quantification of DNA that is the product of amplification reactions, and in the detection of variant DNA (e.g. polymorphisms or mutations). Due in large part to the complex structures and large sizes of such molecules, however, none of the separation techniques devised to date
15 have proven wholly satisfactory.

Traditionally, polynucleotide separations have been performed using electrophoretic methods, such as slab gel electrophoresis or, more recently, capillary electrophoresis. Generally, these methods involve passing an electric current through a medium into which a mixture
20 containing the species of interest has been injected. Each kind of molecule travels through the medium at a different rate, depending upon its electrical charge and size. Unfortunately, the electrophoretic methods are associated with certain disadvantages. For example, slab gel electrophoresis suffers the drawbacks of relatively low speed, difficulty in detection of samples, poor quantitation, and is labor intensive. Although faster and less labor intensive, capillary
25 electrophoresis has suffered from irreproducibility of separations due to changes in the capillary performance and relatively poor quantitation.

Liquid chromatography has provided an alternative to the electrophoretic separation methods. Generally, the liquid chromatographic methods rely on differences in partitioning behavior between a flowing mobile phase and a stationary phase to separate the components in a
30 mixture. A column tube, or other support, holds the stationary phase and the mobile phase carries the sample through it. Sample components that partition strongly into the stationary phase spend a greater amount of time in the column and are separated from components that stay predominantly in the mobile phase and pass through the column faster. As the components elute from the column they can be quantified by a detector and/or collected for further analysis.

Typical stationary phases, and their interactions with the solutes, used in liquid chromatography are:

NAME	STATIONARY PHASE	INTERACTION
Size-Exclusion	Porous inert particles	Samples are separated by virtue of their size in solution; different sized molecules will have different total transit times through the column.
Ion-Exchange	Ionic groups on a resin	Sample ions will exchange with ions already on the ionogenic group of the packing; retention is based on the affinity of different ions for the site and on a number of other solution parameters (pH, ionic strength, counterion type, etc.).
Reverse-Phase	Non-polar groups on a resin	Samples are separated based on hydrophobic interactions with the stationary phase.

5 Although the liquid chromatographic methods have some advantages over electrophoretic separation techniques, they are not without their shortcomings. Size-exclusion chromatography suffers from low resolution, as, typically, DNA molecules must differ in size by 50-100% in order to obtain acceptable resolution. Although ion-exchange chromatography offers higher resolution, it can be affected by anomalous elution orders based on DNA sequence
10 composition. Also with ion-exchange chromatography, the eluted DNA is often heavily contaminated with nonvolatile buffers that can further complicate sample recovery. Reverse-phase chromatography is capable of relatively high resolution but, unless special small-diameter particulates are used as the stationary phase, it cannot be performed at a very high speed. Silica-based particulates used in reverse-phase chromatography have suffered from low speed and
15 instability at high pH conditions. Polymeric particulates have not been able to provide a high recovery of sample components or high separation speeds.

With particular regard to DNA separations, a technique known as reverse-phase ion-pair high performance liquid chromatography (RP-IP HPLC) has provided a limited amount of relief from some of the problems discussed above. For example, RP-IP HPLC avoids the problem of
20 nomalous elution orders often encountered with packed beds bearing strong-anion exchangers. In RP-IP HPLC, the stationary phase typically consists of discrete particles bearing hydrophobic surface groups that are packed into a column. The eluent contains a cationic species, such as triethylammonium ion (0.1M), capable of interacting with the negatively charged phosphate groups on DNA and also with the hydrophobic surface of the particles in the column. Thus, the

cationic species can be thought of as a bridging molecule between DNA and the column. As the mobile phase is made progressively more organic, e.g., with increasing concentration of acetonitrile, the DNA fragments are eluted in order of size.

Despite the advantages of RP-IP HPLC for DNA separations, the technique nevertheless suffers from problems common to all liquid chromatographic techniques wherein small particles (e.g., beads) are packed to form a bed in a column tube. For example, the production of particulate separation media can be complex and time-consuming. Once prepared, it can be difficult to pack the particles in columns in a reproducible and efficient manner. In particular, it has been difficult to pack efficient columns of small dimensions, such as columns less than 1 mm in diameter. Columns having non-circular cross-sections, such as polygonal cross-sections (e.g., thin-layer or rectangular), would be extremely difficult to prepare from particulate packing materials. Also, columns based on packed beads can fail due to shifting of packing material and the development of channels or voids. As an additional disadvantage, the use of small particles often leads to high column operating pressures, which necessitate column tubes, pumps, injectors and other components capable of containing fluid pressures of 3,000 psi or greater.

Current chromatographic theory predicts that, for beds of packed particles, separation efficiency will be determined by the diffusional distance for mass transfer of sample molecule to the stationary phase. This effect is easily modeled based on the known geometry of the particles used in such beds. According to such theory, maximum resolution will occur when the stationary phase has pore diameters of at least 3 times the Stokes' diameter of the molecule to be separated. This theory is based on the assumption that the molecule will be transported to the stationary phase by a diffusive process and that smaller pores would cause hindered diffusion. For DNA separations, this means that for a sample of 1,000 base pairs in size, a pore diameter of at least 1 micrometer will be needed. The need for such large pores practically eliminates the use of porous particulate materials packed in a support for the separation of DNA, as such matrices lack the required physical strength to be used at the operating pressures encountered in high performance liquid chromatography.

Nonporous particulate materials are preferred for DNA separations due to the reduction in diffusion distance compared to porous packings. For nonporous packings, the pore diameter is determined by the interstitial dimensions of the packed bed. The interstitial dimension is approximately 1/3 of the diameter of a spherical packing particle. A lower limit to the pore diameter may be imposed by the need to avoid trapping or shearing of larger DNA molecules. A higher limit will be imposed by the loss of efficiency that occurs when using larger particles.

Separation using larger particles would be advantageous because of the lower operating pressures involved, but the loss in separation efficiency is too great.

As a further disadvantage, spherical packings can be packed into stable beds only at densities approximating an interstitial void fraction of about 0.4. Although somewhat more variable, nonspherical packings are also packed optimally at void fractions of about 0.4. Moreover, packed-particulate beds have fixed surface areas, fixed interstitial distances, and fixed pressure drops determined by the particle diameter of the packing material. Since DNA has a physical size approximating 0.34 micron per 1,000 base pairs of length and efficiency will be highest when the interstitial distance is 3-10 times the Stokes' diameter of the molecules being separated, a column designed for DNA of 1,000 base pairs could require an interstitial distance of 1-3 microns. Columns with packing of 3-10 micrometers in diameter would provide such distances. A column packed with 3 micrometer packings will have high operating pressures in use, whereas a column packed with 10 micrometer packings will show limited efficiency due to longer diffusional paths and lower binding capacity due to a decreased surface area. While columns packed with very small particles, such as 1 micrometer diameter, could be useful for samples up to 300 base pairs in length, column operating pressures would be very high and DNA larger than 300 base pairs could be sheared or trapped. A typical column of packed beads uses particles of 2.1 micrometers in diameter and has high operating pressure under typical use.

The above theory relating to beds of packed particles is not particularly useful for predicting the behavior of macromolecules in continuous monolithic beds, where mass transport may be a combination of diffusive and convective processes.

The present invention, which teaches monolithic beds for resolving mixtures containing polynucleotides, is based in part on the discovery that monoliths provide reduced pressure drops corresponding to the use of large-particle stationary phases while maintaining the separation resolution of columns packed with small spherical particles. More particularly, it has been discovered that reversed-phase monolithic matrices can provide an improved method for the high speed separation of DNA molecules and that such separations can be performed with high resolution at greatly reduced operating pressures compared to previously available methods. This surprising finding now permits the high-resolution separation of polynucleotides under conditions not possible with preexisting technology. Moreover, the monolithic columns of the present invention can be constructed with stationary phase geometries significantly different than those available with packed beds. The effects of such novel geometries on the separation of macromolecules have not been predicted so far by current chromatographic theory.

The monolithic columns of the present invention provide all of the advantages of the previous best technology for polynucleotide separations (i.e., packed beds of alkylated nonporous polymer beads), without the need to tediously prepare beads and pack them into efficient columns. The columns produced by the current invention are easily prepared using
5 simple processes and once prepared, cannot fail through shifting within a packed bed because there are no individual beads to shift position.

In addition to the improved ease of manufacturing of the new columns and lack of bead shifting, the monolithic columns described herein provide a surprising advantage over the existing technology in that they can offer at least 58% better resolution than that expected for a
10 column of packed spheres when normalized for operating pressures.

SUMMARY OF THE INVENTION

One aspect of the present invention provides a method for resolving a mixture containing at least one polynucleotide (e.g., DNA and/or RNA). According to the method, the mixture is
15 passed through a monolithic polymer matrix held in a stationary fashion by a support. The mixture is separated by ion-pair reverse-phase chromatography.

In one embodiment, the monolithic polymer matrix has hydrophobic surface groups. The monolithic polymer matrix can be comprised, at least in part, of a polymer selected from the group consisting of polymethacrylates and polystyrenes. In one embodiment, the polymer is a
20 polymethacrylate.

According to one embodiment, the monolithic polymer matrix is formed from a polymerization mixture including a hydrophobic monomer, a crosslinking agent, and a porogen. The porogen may be (i) a porogenic solvent, (ii) a mixture of porogenic solvents, or (iii) one or more porogenic solvents containing at least one polymeric additive that contributes to pore
25 formation. The hydrophobic monomer can be an alkyl methacrylate.

In one embodiment, the method further includes the step of passing an eluant containing an ion-pairing agent through the monolithic matrix. The separation is carried out under the driving force of a reasonable pressure (e.g., less than about 5,000 psi).

For the support, one embodiment contemplates the use of a column tube having a
30 circular cross-section. Another embodiment contemplates the use of a column tube having a non-circular, e.g., polygonal, cross-section.

An additional embodiment contemplates the use of a plate as the support. The monolithic polymer matrix may fill a channel formed in the plate, or it may take the form of a thin film on the plate.

Still a further embodiment contemplates the use of a chip (e.g., as fabricated by techniques employed in the semiconductor arts) as the support. In this embodiment, the matrix is held in a microfabricated channel formed in the chip. In a related embodiment, a plurality of microfabricated channels are formed in the chip, and multiple separations are carried out in a substantially simultaneous fashion on the chip.

Another aspect of the invention provides a chromatographic apparatus comprising a support holding a macroporous monolithic methacrylate-based polymer matrix. In one embodiment, the polymer matrix has a hydrophobic surface capable of interacting with hydrophobic groups of an ion-pairing agent for resolving polynucleotides by reverse-phase ion-pair chromatography. The polymer matrix may have a relatively high void fraction (e.g., greater than about 0.6).

A further aspect of the invention provides kits for resolving polynucleotides by reverse-phase ion-pair chromatography.

In one embodiment, the kit includes: (i) a polymerization mixture including a monomer having hydrophobic surface groups, a crosslinking agent, and a porogen; and (ii) an ion-pairing agent capable of interacting with negatively charged phosphate groups of the polynucleotides and also with the hydrophobic surface groups of the monomer.

In another embodiment, the kit includes: (i) a monolithic polymer matrix having hydrophobic surface groups held in a stationary fashion by a support; and (ii) an ion-pairing agent capable of interacting with negatively charged phosphate groups of the polynucleotides and also with the hydrophobic surface groups of the monomer.

These and other features and advantages of the present invention will become clear from the following description.

BRIEF DESCRIPTION OF THE DRAWINGS

The structure and manner of operation of the invention, together with the further objects and advantages thereof, may best be understood by reference to the following description taken in conjunction with the accompanying drawings, in which:

Figure 1 is a chromatogram showing the separation of oligothymidylic acids between 12 to 18 units in length on a C6 monolithic column constructed in accordance with an embodiment of the present invention.

Figure 2A is a chromatogram showing the separation of double-stranded DNA fragments on a C12 monolithic column constructed in accordance with an embodiment of the present invention.

Figure 2B is a chromatogram showing results, for comparative purposes, of a separation of double-stranded DNA fragments like those of Figure 2A carried out on a column packed with 2.1 micrometer nonporous beads.

Figure 3A is a chromatogram showing the separation of homoduplex DNA fragments 304 base pairs in length on a porous monolithic C12 column constructed in accordance with an embodiment of the present invention.

Figure 3B is a chromatogram showing the separation of a mixture containing the same type of homoduplex DNA fragments of Figure 3A as well as a variant sequence containing a single base pair substitution on a porous monolithic C12 column constructed in accordance with an embodiment of the present invention.

DEFINITIONS

As used here, the term "polynucleotide" refers to a polymer of ribonucleic acid (RNA) or deoxyribonucleic acid (DNA), which can be single- or double-stranded, optionally incorporating synthetic, non-natural, or altered nucleotides capable of incorporation into DNA or RNA polymers, e.g., methylated nucleotides and nucleotide analogs. Polynucleotides may have any three-dimensional structure, and may optionally be partially or fully denatured. The following are non-limiting examples of polynucleotides: a gene or gene fragment (e.g., restriction fragments), exons, introns, messenger RNA, transfer RNA, ribosomal RNA, ribozymes, cDNA, recombinant polynucleotides, branched polynucleotides, plasmids, vectors, isolated DNA of any sequence, isolated RNA of any sequence, nucleic acid probes, and primers.

The term "columns," as used herein, is intended to include devices where a fluid mobile phase is transported through a stationary bed, regardless of the physical cross-section or dimension of the bed.

The "permeability" of a column bed is a measure of the abundance of large-diameter pores.

DETAILED DESCRIPTION OF THE INVENTION

The following discussion of the preferred embodiments of the present invention is merely exemplary in nature. Accordingly, this discussion is in no way intended to limit the scope of the invention, application of the invention, or the uses of the invention.

The present invention provides a monolithic bed, and method of making and using the same, for resolving bio-organic molecules.

The columns of the invention are prepared from a polymerization mixture which, in one embodiment, includes (1) a monomer, (2) a crosslinking agent, and (3) a porogen (e.g., a porogenic solvent or mixture of porogenic components). In this embodiment, the mixture is placed in a suitably-shaped mold, and subjected to the influence of a polymerization initiator to start a polymerization process which finally yields a macroporous polymer matrix which contains porosity such that a liquid can be passed through the matrix under the driving force of a reasonable pressure (e.g., less than about 5,000 psi).

A monomer, or combination of monomers, is chosen such that the polymerized matrix will include surface groups that can interact with polynucleotides to provide separation based on ion-pair chromatography. In one preferred embodiment, a species bearing hydrophobic surface groups is utilized as the monomer. Optionally, the monomer may be modified to exhibit the desired degree of hydrophobicity. For example, appropriate ligands may be covalently attached to the monomer, by methods known in the art, to improve its effectiveness as a medium for reverse-phase chromatography. Alternatively, or in addition, the polymerized matrix itself may be treated to attach ligands imparting the desired degree of hydrophobicity thereto. If the monomer, or combination of monomers, chosen for use in the polymerization mixture does not otherwise exhibit the desired hydrophobic characteristics, then treatment to add appropriate ligands (e.g., aliphatic surface groups) may be required in order to render the column useful for reverse-phase separations.

In one embodiment, the monomer utilized in the polymerization mixture bears at least one type of alkyl group capable of serving as a hydrophobic group for reversed-phase chromatography. Preferred alkyl groups are those having from about 3 - 30 carbons, and most preferably within the range of about 4 to 18 carbons. Exemplary monomers useful for practicing the invention include hexyl methacrylate, octyl methacrylate, and dodecyl methacrylate. The invention also contemplates the use of a styrene monomer.

Any suitable crosslinking agents known to those skilled in art may be employed in forming the monolithic matrix of the invention. Preferred crosslinking monomers contain at least two carbon-carbon double bonds capable of polymerization in the presence of an initiator. Exemplary crosslinking monomers include divinyl benzene, butadiene, trimethylolpropane trimethacrylate (TRIM), etc.

It should be appreciated that a single species may comprise both the monomer and the crosslinking agent. For example, a hydrophobic crosslinker may serve both of these roles. In this regard, one embodiment of the present invention contemplates the use of TRIM as the only monomer in the polymerization mixture, as well as the only crosslinking agent.

The monomer, or combination of monomers, is generally present in the polymerization mixture in an amount of from about 20 to 80 vol. %, and more preferably in an amount of from about 35 to 50 vol. %.

Conventional free-radical generating polymerization initiators may be employed to
5 initiate polymerization. Examples of suitable initiators include peroxides such as OO-t-amyl-O-(2ethylhexyl)monoperoxy carbonate, dipropylperoxydicarbonate, and benzoyl peroxide, as well as azo compounds such as azobisisobutyronitrile, 2,2'-azobis(2-amidinopropane) dihydrochloride, and 2,2'-azobis(isobutyramide) dihydrate. The initiator is generally present in the polymerization mixture in an amount of from about 0.1 to 2 % by
10 weight of the monomers.

The porogen used may be selected from a variety of different types of materials. The porogen can be (i) a single porogenic solvent, (ii) a mixture of porogenic solvents, or (iii) one or more solvents containing at least one polymeric additive that contributes to pore formation. Suitable liquid porogens include aliphatic hydrocarbons, aromatic hydrocarbons, esters,
15 alcohols, ketones, ethers, solutions of soluble polymers, and mixtures thereof. Exemplary porogenic solvents include isooctane and isooctane with varying percentages of 2-octanone, toluene, or ethyl propionate. Exemplary polymeric additives that contribute to pore formation include polymethyl methacrylate and polystyrene. The porogen is generally present in the polymerization mixture in an amount of from about 20 to 80 vol %, more preferably from about
20 50 to 65 vol %.

For TRIM-based polymerization mixtures, highly permeable monoliths will result, for example, from the use of pure isooctane as a porogenic solvent. Lower permeability will result, for example, from addition of 5-20% of other solvents, such as 2-octanone, toluene, and/or ethyl propionate, to the isooctane. Permeability may also be reduced by increasing the ratio of
25 hydrophobic monomer to crosslinker, and by decreasing the proportion of porogenic solvent in the mixture. Additionally, the choice of initiator may be used as a means to control the pore distribution.

In an exemplary embodiment, the monolithic matrix is prepared from a polymerization mixture including an alkyl methacrylate, an alkane porogenic solvent or mixture of porogenic
30 components, and a free radical initiator. For example, a polymerization mixture was prepared using trimethylolpropane trimethacrylate, an alkyl methacrylate, isooctane, and azobisisobutyronitrile. The mixture was poured into an empty HPLC column tube, capped, and

polymerized at 65-70°C for 8-24 hours. The polymerized matrix was then equipped with endfittings and flushed with solvent to remove unreacted components.

A typical monolithic column constructed in accordance with the present invention will have pores in the less than 5,000nm range, down to about 10nm. The size of larger pores can be
5 determined using very large DNA and/or microscopic exam. For example, the columns of the invention have been used to separate DNA products of 2,072, 2,647, and 3,147 base pairs in length. The largest of these would correspond to a molecular size of at least 1 micron.

Accordingly, the monolithic column used to separate this DNA would be expected to include pores having a diameter of at least 1 micron. This is in agreement with permeability calculations
10 that indicate an apparent particle diameter of 6 microns, or a pore size of about 2 microns. Microscopic exam revealed that a typical matrix of the invention includes small globules of about 1-2 microns in diameter that are fused into continuous structures with pores in the 1-5 micron size range. This is consistent with the estimated pore size based on permeability and DNA fragment chromatography.

Columns of the present invention have also been used to separate DNA down to about 17
15 base pairs. A relatively small DNA of 100 base pairs in length would have a size of only 34nm. So, the high resolution made possible by the present invention is preserved for columns with pores up to at least about 170 times the length of the DNA molecules to be separated. Without committing to any particular theory, it may be this unusual feature that accounts for the low
20 operating pressures possible with the columns of the invention.

Once prepared, the monolithic matrix of the invention is useful for resolving bio-organic molecules, for example, by gradient or isocratic liquid chromatography. In an exemplary use, a column of the invention, prepared as described above, is employed to carry out a separation of polynucleotides contained in a sample. In one embodiment, water and acetonitrile, both
25 containing an ion-pairing agent, are used in gradient liquid chromatography to elute polynucleotides injected into the column.

Conventional ion-pairing agents capable of forming ion pairs with nucleic acids may be used in the present invention. Ion-pairing agents, suitable for practicing the present invention, include cationic hydrophobic species such as alkylammonium salts of organic or inorganic acids,
30 for example tetramethyl, tetraethyl, tetrapropyl and tetrabutyl ammonium acetates, halides, etc. Dimethylbutylammonium, dimethylhexylammonium, dimethylcyclohexylammonium and diisopropylammonium acetates, among others, are effective ion-pairing agents. TEAA (triethylammonium acetate) was found to be an effective ion-pairing agent in both methacrylate-

and styrene-based columns. Tetrabutylammonium bromide was found to be an effective ion-pairing agent for the separation of DNA fragments of length up to at least 1,000 base pairs.

A variety of support structures may be used with the monolithic matrix of the invention. For example, one embodiment contemplates the use of an elongated column tube. In another
5 embodiment, the monolithic matrix is held in the lumen of a capillary tube. In these embodiments, the matrix extends across the entire cross-sectional area of the tube. The tube may be of any desired cross-section, e.g., circular, polygonal, or other shape. The monolithic matrix may be polymerized in situ within the tube, or it may be formed outside of the tube and then inserted by any suitable means.

10 In alternative embodiments, the monolithic matrix is (i) held in a channel or groove on a plate, or (ii) applied as a thin film across a plate. While the monoliths of the invention may be provided on a substrate or supporting plate of virtually any size and composed of any suitable material, one embodiment of the present invention contemplates using a supporting plate of a standard size, which can be constructed using conventional materials and means. Thus, in this
15 embodiment, an injection molded rectangular plastic plate, the length and width of which conform to the commonly used standard of 5.030" x 3.365" (127.76 mm and 85.47 mm), is preferred. Similarly, while a single plate may support any reasonable number of sites, constructions corresponding to the commonly used "96-well" microtiter plate format are preferred. Thus, one preferred construction includes an 8 x 12 array of sites situated on a
20 standard-sized support plate. Each site may support one or more separate monoliths. The position and spacing of the sites on the support plate may be standard, as well (e.g., spaced about 9mm center-to-center). Utilization of standard outside dimensions for the plate frame, as well as standard spacing for the sites on the plate, facilitates use of the plates with existing equipment, such as automated dispensers or optical readers, if desired. It should be appreciated that such an
25 apparatus is capable of handling multiple simultaneous and parallel separations.

In a further embodiment, the monolithic matrix fills one or more channels formed on a microchip. For example, a plurality of channels can be formed on a glass microchip substrate using standard microfabrication techniques, e.g., photolithographic procedures and chemical wet etching. Optionally, a cover plate can be direct bonded to the substrate over the channels. A
30 plurality of separations can be conducted on multiple samples in a substantially parallel fashion upon a single substrate chip.

Advantageously, the columns of this invention are not limited to the fixed surface areas, pressure drops and interstitial diffusional distances of a packed bed. Because the void fraction can be much higher in the monolithic columns taught herein, all of these factors can be

manipulated for improved performance for a given application. For example, columns can be produced with the same void fraction and widely different pressure drops, or columns could be produced with the same pressure drop but different interstitial distances. In a particular example, some columns produced in this invention performing well for DNA separations have
5 void fractions of about 0.7. A void fraction of 0.7 cannot be produced for nonporous packings by packing discrete particles.

Examples

The Examples are intended to illustrate, but not limit, the scope of the invention.

10

Example 1:

Separation of Single-Stranded Oligonucleotides

A mixture containing 1.0 ml trimethylolpropane trimethacrylate, 0.32 ml hexyl methacrylate, 2.4 ml isooctane, and about 20 mg azobisisobutyronitrile was prepared and
15 injected into empty 4.6 mm ID x 5 cm long HPLC column tubes closed at one end with an endfitting and plug. The filled tube was closed at the other end with an endfitting and plug, then immersed in a water bath at 65°C overnight. After reaction, the plugs and endfittings were removed and endfittings with polyethylene frits attached. The complete column was flushed with tetrahydrofuran.

20

Figure 1 is a chromatogram showing the separation of single-stranded oligothymidylic acids on a C6 monolithic column constructed in the manner just described. Specifically, the sample was 10 microliters of oligothymidylic acids between 12 and 18 units in length. At a flow rate of 2 ml/minute, a gradient of 0-12% acetonitrile in 100mM aqueous triethylammonium acetate, 10mM disodium EDTA, pH 7.0 was used to elute the oligonucleotides. Detection was
25 performed using UV absorbance at 254nm. An extremely low HPLC system pressure of only 150psi was observed during the separation.

Example 2:

Separation of Double-Stranded DNA

30

A mixture containing 1.25 ml trimethylolpropane trimethacrylate, 0.30 ml lauryl methacrylate, 2.6 ml of a mixture of 95% isooctane and 5% toluene and 17 mg azobisisobutyronitrile was prepared and injected into empty 4.6 mm ID x 5 cm long HPLC

column tubes closed at one end with an endfitting and plug. The filled tube was closed at the other end with an endfitting and plug, then immersed in a water bath at 65°C overnight. After reaction, the plugs and endfittings were removed and endfittings with polyethylene frits attached. The complete column was flushed with tetrahydrofuran.

5 Figure 2A is a chromatogram showing the separation of double-stranded DNA fragments on a monolithic C12 column constructed in the manner just described. Specifically, the sample was 3 microliters of pUC18 DNA digested by the MSP I restriction enzyme. At a flow rate of 1.0 ml/minute, a 10 minute gradient of 35%-60% acetonitrile containing 20mM tetrapropylammonium bromide in 20mM aqueous tetrapropylammonium bromide, 2mM
10 disodium EDTA, pH 7.0 was used to elute the DNA fragments. Detection was performed using UV absorbance at 254 nm. At 0.5 ml/min an HPLC system pressure of 50psi was observed. Resolution was calculated for the peaks indicated in Figure 2A by arrows.

For comparative purposes, a similar separation was carried out using a column packed with nonporous polymer spheres. In this regard, Figure 2B is a chromatogram showing the
15 separation of double-stranded DNA fragments on a column packed with 2.1µm diameter nonporous beads. In this comparative experiment, the sample was 3 microliters of pUC18 DNA digested by the MSP I restriction enzyme. At a flow rate of 0.5 ml/minute, a 10 minute gradient of 8.75%-15% acetonitrile in 100mM aqueous triethylammonium acetate, 10mM disodium
20 EDTA, pH 7.0 was used to elute the DNA fragments. Detection was performed using UV absorbance at 254 nm. At 0.5 ml/min an HPLC system pressure of 1340psi was observed. Resolution was calculated for the peaks indicated in Figure 2B by arrows.

The chromatographic data from the above experiments are summarized in Table 1. The resolution of the marked peaks was found to be 4.04 for the monolithic column of Figure 2A and 5.83 for the column packed with nonporous spheres in Figure 2B. Using standard permeability
25 calculations (*Introduction to Modern Liquid Chromatography*, 2nd edition, L.R. Snyder and J.J. Kirkland, John Wiley and Sons, New York, 1979, p. 37), it can be calculated that the column of Figure 2A has an operating pressure equivalent to that of a column packed with 6.22 micron diameter spheres whereas that in Figure 2B would be estimated as 1.20 micron. Based on these
30 different effective particle sizes, the column of Figure 2A has a resolution 58% greater than expected. A critical figure of merit for chromatographic separations is the efficiency or resolution per unit pressure. It can be seen from the data of Table 1 that the monolithic column offers an order of magnitude increase in resolution per unit pressure compared to the column packed with nonporous spheres.

Table 1

	Column with Nonporous Spherical Packing	Column with C12 Monolithic Polymer
Retention Time Peak 1 (min.)	6.80	9.36
Area Peak 1 ($\mu\text{V}\cdot\text{sec}$)	80678.00	84592.00
Height Peak 1 (μV)	11370.00	7438.00
Retention Time Peak 2 (min.)	7.52	10.10
Area Peak 2 ($\mu\text{V}\cdot\text{sec}$)	103115.00	103644.00
Height Peak 2 (μV)	13348.00	9779.00
Resolution	5.83	4.04
Column Pressure (psi)	1340.00	100.00
Apparent Particle Size (μm)	1.20	6.20
Expected Resolution	5.83	2.57
Excess Resolution %	0.00	58.00
Resolution/1,000 psi	4.35	40.42

Example 3:**Separation of Partially Denatured Double-Stranded Polynucleotides**

5

The present invention also makes possible the separation of partially denatured double-stranded polynucleotides. As shown in Figures 3A and 3B, a porous monolithic column was used to separate DNA fragments 304 base pairs in length. In Figure 3A, the sample contained a single type of DNA, whereas in Figure 3B the sample contained a mixture of the type seen in

10 Figure 3A and a variant sequence containing a single base pair substitution. At the selected temperature, the sample of Figure 3B shows a second peak that represents partially denatured DNA containing the single base pair substitution.

Specifically, with regard to Figure 3A, homoduplex DNA with sequence 304 base pairs in length was separated on a monolithic C12 column, prepared as described above. In carrying

15 out the separation, the conditions as set out in Table 2, below, were observed:

Table 2

Mobile Phase:	A: 20mM tetrapropylammonium bromide + 2mM disodium EDTA in water, pH 7.0 B: 20mM tetrapropylammonium bromide in acetonitrile
Gradient:	50-65% B in A over 7 minutes
Flow Rate:	0.75 ml/min
Separation temperature:	43° C
Detection:	UV, 254nm

Similar conditions were observed in obtaining the data of Figure 3B, except that the sample contained, in addition to the 304 base pair homoduplex DNA of Figure 3A, a variant heteroduplex DNA species having a single base pair substitution. The peak marked with the arrow in Figure 3B indicates the presence of this variant DNA.

Comparative Example A

US Patent No. 5,334,310 to Frechet et al. suggests that one solution to some of the aforementioned problems associated with column beds of packed particulate materials would be the use of a continuous bed for the separation of large molecules. However, the '310 patent offers no particulars or guidance to enable the selection of a suitable matrix for the separation of DNA by the most advantageous method, RP-IP HPLC.

For comparative purposes, columns were constructed in accordance with Examples III and VI of the '310 patent. Briefly, these examples describe monolithic columns which are hydrophobic in nature. After the polymerizations of these compositions, end fittings were attached and the columns flushed with methanol, as described in the '310 patent. The composition produced by Example III of the '310 patent was translucent in appearance and had a very high operating pressure (greater than 2,000psi at 0.25ml/min with methanol), precluding its use in practical HPLC of DNA. The composition produced by Example VI of the '310 patent was white and had a relatively low operating pressure. However, this latter column did not provide useful separations of DNA restriction fragments under reversed-phase ion-pairing conditions. No typical pattern of peaks was observed when a separation was attempted under conditions that would provide a useful separation using the matrices of the present invention.

These findings are in accord with previous suggestions in the literature that columns with unmodified polystyrene/divinylbenzene structures are not desirable for DNA separations.

Those skilled in the art can now appreciate from the foregoing description that the broad teachings of the present invention can be implemented in a variety of forms. Therefore, while
5 this invention has been described in connection with particular embodiments and examples thereof, the true scope of the invention should not be so limited. Various changes and modification may be made without departing from the scope of the invention, as defined by the appended claims.

WHAT IS CLAIMED IS:

1. A method for resolving a mixture containing at least one polynucleotide, comprising:
passing said mixture containing at least one polynucleotide through a monolithic
polymer matrix held in a stationary fashion by a support, and
5 separating said mixture being passed through said matrix by ion-pair reverse-phase
chromatography.
2. The method of claim 1, wherein said monolithic polymer matrix has hydrophobic surface
groups.
- 10 3. The method of claim 2, further comprising the step of passing an eluant containing an
ion-pairing agent through said monolithic matrix, said ion-pairing agent being an
alkylammonium salt.
- 15 4. The method of claim 2, wherein said monolithic polymer matrix is comprised, at least in
part, of a polymer selected from the group consisting of polymethacrylates and polystyrenes.
5. The method of claim 4, wherein said polymer is a polymethacrylate.
- 20 6. The method of claim 5, wherein said monolithic polymer matrix is formed from a
polymerization mixture including a hydrophobic monomer, a crosslinking agent, and a porogen.
7. The method of claim 6, wherein said hydrophobic monomer is an alkyl methacrylate.
- 25 8. The method of claim 6, wherein said at least one polynucleotide is selected from the
group consisting of DNA and RNA.
9. The method of claim 6, further comprising the step of passing an eluant containing an
ion-pairing agent through said monolithic matrix, said ion-pairing agent being capable of
30 interacting with negatively charged phosphate groups of said at least one polynucleotide and
also with said hydrophobic surface of said monolithic polymer matrix.
10. The method of claim 9, wherein the mixture is subjected to a driving force of less than
about 3,000 psi.

11. The method of claim 9, wherein said support is a column tube having a circular cross-section.
12. The method of claim 9, wherein said support is a column tube having a polygonal cross-section.
13. The method of claim 9, wherein said support is a plate.
14. The method of claim 13, wherein said monolithic polymer matrix is held in a channel formed in said plate.
15. The method of claim 13, wherein said monolithic polymer matrix takes the form of a thin film on said plate.
16. The method of claim 9, wherein said support is a chip and said matrix is held in a microfabricated channel formed in said chip.
17. The method of claim 16, wherein a plurality of microfabricated channels are formed in said chip, and wherein multiple separations are carried out in a substantially simultaneous fashion on said chip.
18. A chromatographic apparatus, comprising:
a support holding a macroporous monolithic methacrylate-based polymer matrix;
wherein said polymer matrix has a hydrophobic surface capable of interacting with hydrophobic groups of an ion-pairing agent for resolving polynucleotides by reverse-phase ion-pair chromatography.
19. The chromatographic column of claim 17, wherein the polymer matrix has a void fraction of greater than 0.6.
20. A kit for resolving polynucleotides by reverse-phase ion-pair chromatography, comprising:
a polymerization mixture including a monomer having hydrophobic surface groups, a crosslinking agent, and a porogen; and

an ion-pairing agent capable of interacting with negatively charged phosphate groups of said polynucleotides and also with said hydrophobic surface groups of said monomer.

21. A kit for resolving polynucleotides by reverse-phase ion-pair chromatography,

5 comprising:

a monolithic polymer matrix having hydrophobic surface groups held in a stationary fashion by a support; and

an ion-pairing agent capable of interacting with negatively charged phosphate groups of said polynucleotides and also with said hydrophobic surface groups of said monomer.

10

1/3




FIG. 1

2/3




FIG. 2A




FIG. 2B

3/3




FIG. 3A




FIG. 3B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/20596

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C12N15/10 B01J20/28 B01D15/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C12N B01J B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 19347 A (PHARMACIA BIOTECH AB ;ALLMER KLAS (SE); BERGGREN EVA (SE); ERIKSSO) 29 May 1997 (1997-05-29)	1-5, 18, 19
Y	page 5, line 33-page 6, line 11 page 7, line 36-page 8, line 2 page 8, line 11-22 page 11, line 3-18 claims 7, 14-18	6-17, 21
X	US 5 334 310 A (FRECHET JEAN M J ET AL) 2 August 1994 (1994-08-02)	18, 19
Y	cited in the application column 5, line 20-55	6-17, 20
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

28 January 2000

Date of mailing of the international search report

14/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

ALCONADA RODRIG., A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/20596

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	LIAO J L ET AL: "Continuous beds for microchromatography: reversed-phase chromatography." ANALYTICAL BIOCHEMISTRY, (1996 FEB 1) 234 (1) 27-30. , XP000867339	18,19
A	the whole document	1-17,20,21
Y	WO 94 11305 A (SARASEP INC) 26 May 1994 (1994-05-26)	20,21
A	page 5, paragraph 2 page 11, paragraph 2 page 15, paragraph 3	3,9-17
Y	GIOVANNINI R ET AL: "High-performance membrane chromatography of supercoiled plasmid DNA." ANALYTICAL CHEMISTRY, (1998 AUG 15) 70 (16) 3348-54. , XP000867169 the whole document	13-15
A	BIO-RAD LABORATORIES: "Nucleotide and oligonucleotide separations on an UNO Q1 ion exchange column" BIO-RAD TECHNICAL BULLETIN 2352 (ONLINE), 24 July 1998 (1998-07-24), pages 1-4, XP002129107 Available from Internet URL: < http://www.bio-rad.com/templates/html/73650_manual.html >	1-21

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/20596

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9719347 A	29-05-1997	EP 0862737 A	09-09-1998
US 5334310 A	02-08-1994	US 5453185 A	26-09-1995
		DE 69211010 D	27-06-1996
		DE 69211010 T	23-01-1997
		EP 0609373 A	10-08-1994
		JP 7501140 T	02-02-1995
		WO 9307945 A	29-04-1993
WO 9411305 A	26-05-1994	AT 398973 B	27-02-1995
		AT 228592 A	15-07-1994
		AT 176454 T	15-02-1999
		AU 5667894 A	08-06-1994
		DE 69323435 D	18-03-1999
		DE 69323435 T	01-07-1999
		EP 0669897 A	06-09-1995
		ES 2130396 T	01-07-1999
		GR 3029863 T	30-07-1999
		JP 8505700 T	18-06-1996
		US 5585236 A	17-12-1996

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☒ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.